



Nota de aplicação

Abr 28 2022

Thickness Measurement of Automobile Fuel Tanks




Application: Measurement of individual layers and total thickness in multilayer plastic automobile fuel tanks.

Background: Most contemporary automobile fuel tanks are fabricated with a multilayer plastic construction, typically made of two structural layers of high density polyethylene (HDPE) surrounding a thin gas barrier layer made of ethylene vinyl alcohol (EVOH). The purpose of the barrier layer is to prevent the slow leakage of gasoline vapor through the polyethylene wall. The HDPE structural layers are typically in the thickness range 0.1 in. to 0.2 in. (2.5 to 5 mm), and the EVOH barrier layer is typically 0.004 in. to 0.012 in. (0.1 to 0.3 mm). Tank manufacturers need to measure both the thickness and the depth of the barrier layer.


Equipment: The **Model 38DL PLUS ultrasonic thickness gage** with the Multi-Measurement software option is recommended for simultaneous measurement of individual layers and total tank thickness in this application. With this software, the 38DL PLUS gage is capable of using separately programmed setups (including sound velocity, gain, and blanking settings) for each layer being measured to optimize performance. In this test, the gage is most often used with an M2017-RM (20 MHz) delay line transducer. Contact Olympus for gage setup assistance.

Typical Procedure: The waveforms below show measurements of structural and barrier layers in a typical automobile fuel tank using appropriate setups. The gage's frequency-based barrier measurement mode is used to read the barrier layer whenever its thickness is less than approximately 0.010 in. (0.25 mm). Barrier depth is measured with a conventional Mode 2 setup, and the thickness of the inner polyethylene layer is also measured in Mode 2. Thick barrier layers, greater than approximately 0.010 in. (0.25 mm) may also be measured in Mode 2. Note that because of low pass filtering effects in the outer polyethylene wall, the minimum measurable barrier thickness will usually be approximately 0.004 in. (0.100 mm).


The reflection ratio at the boundary between any two materials is determined by the relative acoustic impedances of those materials. Because virgin and regrind material have essentially identical acoustic impedances, it is not possible to separately measure regrind layers. Also, adhesive layers adjacent to barrier layers are generally too thin and/or too closely impedance matched to measure with ultrasonic techniques and cannot be resolved.



outer polyethylene layer



barrier layer (frequency domain measurement)



inner polyethylene layer

As with any ultrasonic thickness measurement, accuracy is dependent on proper sound velocity calibration. Velocity calibration must be performed for each material being measured, on samples of known thickness.

Related Product



38DL PLUS

O versátil medidor 38DL PLUS™ pode ser usado com transdutores de elemento duplo para a medição da espessura de tubos corroídos e para medições de espessura muito precisas de materiais finos ou multicamadas com um transdutor de elemento único.

Saiba mais ► [https://www.olympus-ims.com/\\$lang/38dl-plus/](https://www.olympus-ims.com/$lang/38dl-plus/)



45MG

O medidor de espessura ultrassônico avançado 45MG é fornecido com recursos de medição padrão e opções de software. Essa ferramenta de medição de espessura exclusiva é compatível com a nossa linha completa de transdutores de medidores de espessura de elemento duplo e elemento único.

Saiba mais ► <https://www.olympus-ims.com/pt/45mg/>



Magna-Mike 8600

O medidor de espessura de efeito Hall Magna-Mike™ 8600 usa uma sonda magnética para realizar medições precisas da espessura de materiais finos e não ferrosos, como garrafas de plástico.

Saiba mais ► <https://www.olympus-ims.com/magna-mike8600/>



72DL PLUS

O medidor de espessura ultrassônico avançado 72DL PLUS™ oferece medições de espessura precisas em alta velocidade em um dispositivo portátil e fácil de usar. Compatível com transdutores de elemento único de até 125 MHz, esta ferramenta de medição de espessura inovadora é ideal para determinar a espessura de materiais ultrafinos, incluindo tintas multicamadas, revestimentos e plásticos. Ele pode exibir simultaneamente a espessura de até 6 camadas.

Saiba mais ► <https://www.olympus-ims.com/72dl-plus/>